

ISLAND ACRYLIC TINTING COLOR**DESCRIPTION :**

Island Acrylic Tinting Color is mixed from quality tested Thermoplastic acrylic resins and colored pigments for maximum durability and protection. It has inherent hardness, excellent intercoat adhesion, resistant to gasoline, acid and common chemicals. It also dries rapidly with lasting full gloss.

USE :

For automotive refinishing and other transport vehicles, appliances and other industrial application where fine finish is desired.

COLORS :

2610 Lemon Yellow
2611 Medium Yellow
2612 Yellow Oxide
2613 Yellow Toner
2620 Orange
2630 Red Oxide
2631 Bon Red

2632 Astral Red
2633 Candy Red
2634 Permanent Red
2635 Red Toner
2650 Phthalo Green
2670 Phthalo Blue
2681 Mixing Black

APPLICATION :

Spray

Island Acrylic Tinting Color can be used both as tinting colors and finish colors as well.

REDUCER :

Island Acrylic Thinner.

MIX RATIO :

Mix one (1) part Acrylic Paint to approximately two (2) parts Acrylic Thinner.

The information in this data sheet is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve users from the responsibility of carrying out their own tests neither do they imply any legally binding assurance of certain properties or suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any propriety rights and existing laws and legislation are observed.

DRYING TIME :

Dry to handle : ½ hour

Dry to recoat : 1-2 hours depending on weather condition.

Dry to rub : about two (2) days

SURFACE PREPARATION :

- **Normal de-rusting, de-greasing / sanding preparation for metal surfaces.**
- **Primer- Epoxy Zinc Chromate Yellow, Red Oxide or Gray depending on type of metal.**
- **Tie Coat-Pure Acrylic Primer Surfacer Gray**
- **Finish Coat- Colorcoat**

COVERAGE :

White – 12 sq. m. per liter @ 25 microns dry film

Colored – 15.0 sq. m. per liter @ 25 microns dry film

PACKAGING :

1L and 4L lithographed cans

The information in this data sheet is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve users from the responsibility of carrying out their own tests neither do they imply any legally binding assurance of certain properties or suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any propriety rights and existing laws and legislation are observed.